



PROXAN®-CP-A

Two-component primer for polysulphide sealants/joint sealants on special substrates

Uses

PROXAN®- CP-A is a two-component primer for polysulphide sealants/joint sealants in problematic substrates and is intended for use in special applications. It can be used on absorbent and non-absorbent substrates and achieves excellent adhesive properties on freshly cut asphalt and various metals (stainless steel, brass, aluminium). In addition, it can withstand thermal and chemical loads.

Properties

- EP-resin based
- For special applications, e.g. cut asphalt
- Excellent adhesive properties
- High thermal and chemical resistance

Application instructions

Application

The substrate must be dry, free of dust and grease and without any loose components. The surface temperature during application must be at least 3 Kelvin above the dew point temperature. Mix components A and B thoroughly and apply the primer evenly with a brush. After a flash-off time of 2 to 8 hours (depending on weather conditions) the sealant can be introduced. The primer should have dried extensively. Ensure that a film of moisture has not formed on the primer surface due to falling below the dew point temperature.

Weather conditions

The surface temperature during application must be at least 3 Kelvin above the dew point temperature. Ensure that a film of moisture has not formed on the primer surface due to falling below the dew point temperature.

Material consumption

0.02 to 0.04 l per linear metre (depending on joint dimensions)

Storage

Can be stored for 12 months in a dry location at temperatures below +25 °C in a closed original container.

Form of supply

Combi container per 1 litre (Components A and B): 10 containers per box

Technical data

Chemical basis	epoxy resin
Processing time	approx. 60 minutes (at 23 °C, standard conditions)
Flash-off time	approx. 240 minutes (at 23 °C, standard conditions)
Mixing ratio	A : B = 7 : 4 mass portions
Consumption	0.02 to 0.04 l/linear m (depending on joint dimensions)

www.biguma.lt | info@biguma.lt



This product information corresponds to our latest available information. The processor is obliged to test the suitability and application options for the intended purpose.